

TOMBO NO.5700P



| | |
|---|--|
| Our Proposal | : TOMBO NO.5700-P "Hard Setting Cement" |
| Manufacture | : NICHIAS CORPORATION |
| Description | : Hard Setting Cement, composed of inorganic fiber and organic fiber. Recommended for use over insulation to provide a hard surface finish. Asbestos is not included 25 kg. per bag |
| Service Temperature Limits | : Up to 700 C (1300 F) |
| Bulk Density after drying | : 1500 kg/m ³ max. |
| Bending Strength | : 7.0 kgf/cm ² min |
| Linear Shrinkage (at 700C 3 hrs) | : 4.0% max |
| Water to mix Water/Tombo 5700-P | : 120 liters / 100 kg. |
| Thermal Conductivities, Kcal/m.h C | : 0.25 + 0.00010 (0- mean temperature) |
| Coverage | : 25 mm. thick per 100 kgs. 6.3m ² 1" thick per 10 lbs., 30 ft ² |
| Usage | : Finishing cement of Bottom Head with Skirt of Hot Vessel |

NICHIAS Corporation

1-16, shibadaimon 1-chome,
Minato-ku, Tokyo 105-8555 Japan.

